

Laminam 5
Choice 1
PIETRA DI SAVOIA
TECHNICAL SHEET

Properties	Standard	Value
Size	ISO 10545-2	Max deviation on the side +/- 0,5 mm Max deviation on the diagonal +/- 1,0 mm
Weight	Laminam	Average value 14 kg/m ²
Surface quality	ISO 10545-2	> 95%
Water absorption	ISO 10545-3	Average value 0,1%
Breaking load (N)	ISO 10545-4	Average value 1100
Modulus of Rupture (N/mm ²)	ISO 10545-4	Average value 50 (sample size 200x300 mm)
Mohs scale hardness	UNI EN 101	≥ 6
Deep abrasion resistance	ISO 10545-6	≤ 175 mm ³
Linear thermal expansion coefficient (10 ⁻⁶ °C)	ISO 10545-8	6,6
Thermal shock resistance	ISO 10545-9	Resistant
Chemical resistance	ISO 10545-13	No visible effect
Stain resistance	ISO 10545-14	Class 5
Frost resistance	ISO 10545-12	Resistant
Friction coefficient	ASTM C-1028	μ > 0,6
Fire reaction	EN 13501	A1 (according to 96/603/ce as amended)
Slipperiness	DIN 51130	R10

LAMINAM S.p.A.
Via Ghiarola Nuova 258
41042 FIORANO (MO)
C.F./P.IVA 01969990365